

## Avery® MPI™ 2150

Issued: 02-04-2013

### Introduction

Avery **Multi Purpose Inkjet** media 2150 is a lustre white translucent PVC film with a permanent adhesive. It is suitable for use on a variety of super wide format inkjet and airbrush printers using solvent ink.

### Description

Film : 90 micron white translucent PVC film  
Adhesive : permanent, acrylic based  
Backingpaper : Kraft paper, 140 g/m<sup>2</sup>

### Conversion

Avery MPI 2150 is multi-purpose PVC film, developed for use on super wide format printers using solvent based inks.

Avery **MPI-A 2150** rolls are reverse wound on a special core with 4 notches.

In Avery Technical Bulletin 5.15, printer compatability details of Avery Media are listed.

To enhance colour and protect images against UV radiation and abrasion, Avery MPI 2150 is recommended to be overlaminated with Avery® DOL 2000 Gloss, Avery® DOL 2100 Matt or Avery® DOL 2200 Lustre.

For an overview of recommended combinations of DOL films and media, please refer to "[Technical Bulletin 5.3. Recommended combinations of Avery® Overlaminates and Avery® Digital Print Media](#)".

### Uses

- Graphics for internally illuminated signs.
- Window decorations and graphics.

### Features

- Excellent printability and handling on selected printers
- Easy conversion because of dimensionally stable special backing.
- Excellent colour uniformity in reflected and transmitted light.
- Excellent durability.
- Excellent adhesion.

## Physical properties

Features	Test method <sup>1</sup>	Results
Caliper, facefilm	ISO 534	90 micron
Caliper, facefilm + adhesive	ISO 534	120 micron
Dimensional stability	FINAT FTM 14	0.3 mm max
Tensile strength	DIN 53455	27 N/mm <sup>2</sup>
Gloss	ISO 2813, 20°	15%
Adhesion, initial	FINAT FTM-1, stainless steel	±70% of the ultimate values
Adhesion, ultimate	FINAT FTM-1, stainless steel	
	PMMA	900 N/m
	Glass	860 N/m
	Polystyrene	900 N/m
	Stainless steel	900 N/m
Accelerated ageing	DIN 53387	No negative impact on film performance
	100 hours exposure	Self-extinguishing
Flammability		
Shelf life	Stored at 22° C/50-55 % RH	2 years
Durability, unprinted	Vertical exposure	5-7 years

## Temperature range

Features	Test method <sup>1</sup>	Results
Minimum application temperature:		≥ 10 °C
Service temperature:		- 50 °C to + 110 °C
Heat resistance:	3 weeks exposure at 80° C	No negative impact on film performance

**NOTE:** Materials have to be properly dried before further processing, like laminating, varnishing or application. The residual solvents can otherwise change the products' specific features

*For good print and converting result we recommend to let the rolls acclimatize in the print/lamination room at least 24 before printing or converting. Too much temperature or humidity deviation between material and room climate can cause layflatness and/or printability issues.*

*Generally, constant material storage conditions of ideally 20°C (+/-2°C) /50% rh (+/- 5%), without too big climate deviations, will support a more robust and stable printing/converting process. For further details, please refer to TB 1.11.*

### Important

Information on physical and chemical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use. All technical data are subject to change.

### Warranty

Avery® branded materials are manufactured under careful quality control and are warranted to be free from defect in material and workmanship. Any material shown to our satisfaction to be defective at the time of sale will be replaced without charge. Our aggregate liability to the purchaser shall in no circumstances exceed the cost of the defective materials supplied. No salesman, representative or agent is authorised to give any guarantee, warranty, or make any representation contrary to the foregoing.

All Avery® branded materials are sold subject to the above conditions, being part of our standard conditions of sale, a copy of which is available on request.

### 1) Test methods

More information about our test methods can be found on our website.

### 2) Durability

The durability is based on middle European exposure conditions. Actual performance life will depend on substrate preparation, exposure conditions and maintenance of the marking. For instance, in the case of signs facing south; in areas of long high temperature exposure such as southern European countries; in industrially polluted areas or high altitudes, exterior performance will be decreased.